PRE-MIXED SANDED STUCCO



HIGH STRENGTH ASTM C-926

Technical Data Sheet

Description

TradeCraft High Strength Pre-Mixed Sanded Stucco is formulated with Portland Cement certified to meet the requirements of ASTM C-150. All TradeCraft High Strength Pre-Mixed Sanded Stucco is factory blended, designed for exterior grade construction (interior when applicable). Utilizing proprietary chemically engineered admixtures to reduce cracking, increase yield and workability. TradeCraft High Strength Pre-Mixed Sanded Stucco will meet the property requirements of ASTM C-926. No chloride accelerators are used in the mix and all components are compatible with reinforcing steel.

Benefits

- Reduce Waste
- · Reduce Labor and Increase Productivity
- · Reduce Shrinkage and Cracking
- · Factory Blending Offers Consistent Quality
- Easy to Transport
- Excellent for Tight Job Sites
- Factory Technical Support
- Just Add Water
- · Increased Pump Ability
- Also offered with Integral Waterproofing Admixture.
 See Technical data sheet and testing results for TradeCraft High Strength Waterguard Stucco

Suggested Uses

- New Construction
- Restoration and Repair Concrete Block or Brick
- Patching
- For High Strength Pre-Mixed Stucco with Integral Waterproofing see TradeCraft High Strength Waterguard Stucco Tech Data Sheet

Directions for Mixing

TradeCraft High Strength Pre-Mixed Sanded Stucco requires only clean potable water free of any known contaminants. The maximum amount of water can be mixed with this product that is consistent with optimum workability. Once the appropriate amount of water is added, mixing time is 6 minutes in a mechanical batch mixer to ensure consistency and workability of the plaster stucco.

Coverage

An 80 lb bag of Sanded Stucco will cover 20 sq ft, at a thickness of 1/2".

Actual coverage may vary from these estimates due to variability in the sand and trade practices.

Packaging & Yields

TradeCraft High Strength Pre-Mixed Sanded Stucco is available in 80 lb bags. Bulk or Tote bags are produced in selected markets. The unit weight of the dry Sanded Stucco is approximately 105 pounds per cubic foot of dry material, and yield is approximately .80 cubic feet per 80 lb bag. Shelf-life is 12 months when stored in cool dry environment.

TradeCraft High Strength Pre-Mixed Sanded Stucco is available at leading stucco and masonry supply houses throughout the country.

Specifications

	Compressive Strength PSI	
Mix Type	7 Days	28 Days
TradeCraft Stucco		2465.0
Control Mix	2363.5	2885.5
	Average	2675.25

Caution

AVOID CONTACT WITH SKIN INJURIOUS TO EYES. Contains Portland Cement (CAS #65997-15-1). Freshly mixed cement, mortar, concrete, grout, or stucco may cause skin injury including severe alkali burns. If exposed, wash skin promptly and repeatedly for 15 minutes and get prompt medical attention. The use of gloves and protective eye wear is recommended.

Warning Inhalation Hazard: Avoid Inhalation of dust from this product, which contains crystalline silica that causes lung disease and cancer. Use with mechanical ventilation or respiratory protection (dust masks).

KEEP OUT OF REACH OF CHILDREN

EXCLUSION OF INCIDENTAL AND CONSEQUENTIAL DAMAGES Neither the manufacturer nor the retailer of this product shall be liable for any

incidental or consequential damages caused by the use of this product.

