

Mortar Mix

Description

Pakmix[®] Mortar Mix is a specially formulated blend of Masonry cement and fine sand. This product is ideal for use in the laying of brick, block or stone. All ingredients are thoroughly premixed to ensure maximum strength and workability. Simply add water. Pakmix[®] Mortar Mix meets or exceeds the strength requirements of ASTM C-387 for Type N Mortar when used as directed. 750 PSI@ 28 days.

Suggested Uses

- Laying brick
- Setting blocks
- Tuck pointing
- Patching
- Stuccoing
- Repairing chimneys
- Stone work

Preparation

All surfaces should be clean and free of oil, gas, paint, grease, etc. before applying the mix.

Directions for Mixing

Pour the estimated amount of Pakmix[®] Mortar Mix into a clean wheelbarrow, mortar box or similar easy-to-use container. Form a crater with a shovel or hoe in the center of the dry mix. Pour clean water into the crater at a rate of approximately 1 quart per 15 lbs of dry material. If the mix is too stiff, add more water 1 cup at a time. The mix should have the consistency of thick batter.

Items You May Need

- Mortar box or wheelbarrow
- Regular or rectangular trowel
- Shovel or hoe
- Snap line and level
- Hammer
- Chisel

Packaging and Yields

60 lb bag will lay approximately 20 - 8" x 16" blocks or 48 common bricks with a 3/8" joint. Approximately 3/5 cu ft wet volume.

For Best Results

Use only when temperature is 40° F and rising. In cold weather use warm, not hot, water for mixing.

Dampen the block or the repair area before applying the new mortar to prevent premature drying of the new material.

Keep the new mortar damp for at least 3 days by an occasional fine spraying with water.

Clean Up

continued on back

Clean up is easy with soap and water. Clean tools before the material hardens.

Warning

For structural use or to meet code requirements use Pakmix[®] Type S Mortar

60 lb bag



CAUTION • AVOID CONTACT WITH SKIN • INJURIOUS TO EYES Contains Portland Cement (CAS #65997-15-1). Freshly mixed cement, mortar, concrete, grout, or stucco may cause skin injury including severe alkali burns. If exposed, wash skin promptly and repeatedly for 15 minutes and get prompt medical attention. The use of gloves and protective eye wear is recommended. If any cement or cement mixtures get into the eye, rinse immediately and repeatedly with water for 15 minutes and get prompt medical attention.

WARNING INHALATION HAZARD Avoid inhalation of dust from this product, which contains crystalline silica and other chemicals, which may cause lung disease and cancer. Use with mechanical ventilation or respiratory protection (dust mask).

EXCLUSION OF INCIDENTAL AND CONSEQUENTIAL DAMAGES Neither the manufacturer nor the retailer of this product shall be liable for any incidental or consequential damages caused by the use of this product.

KEEP OUT OF REACH OF CHILDREN

DISCLAIMER AND LIMITATION OF LIABILITY This material is warranted to be of good quality. Upon receipt of a claim within one year from the date of sale, defective material will be replaced or the purchase price refunded at the option of the manufacturer. Except for the foregoing, all warranties, express or implied, including merchantability and fitness for a particular purpose, are excluded. No liability is assumed for any consequential, incidental or special damages arising directly or indirectly from the use of the material.